



Global EcoTechnologies, inc

ENDURA-FLEX® 1988 ELASTOMERIC POLYURETHANE

CHEMICAL CONTAINMENT DATA

The following chemical resistance data is offered as a guide as to performance to be expected from a 70-75 mil film of EF-1988 immersed in each substance listed at 75-78°F. As is true for all materials, EF-1988 has chemical and temperature limitations. Testing must be completed for substance applications other than those listed herein. Consult your representative.

CHEMICAL

KEY CODE

ACIDS

SULFURIC ACID, 60%	S
SULFURIC ACID, 30%	S
HYDROCHLORIC ACID, 37%	S
PHOSPHORIC ACID, 85%	S
ACETIC ACID, 60%	D
GLACIAL ACETIC	D
FERROUS CHLORIDE	S
FERRIC CHLORIDE	S
CHLORINE	A

KEY CODES:

A = EXCELLENT

B = GOOD

C = FAIR

D = NOT RECOMMENDED

**S = SATISFACTORY FOR SPLASH, SPILLAGE, AND
SECONDARY CONTAINMENT (96 HOURS)**

ALKALIES

AMMONIUM HYDROXIDE, 30%	S
AMMONIUM HYDROXIDE, (CONC.)	S
SODIUM HYDROXIDE, (>50 Y.)	S

ALIPHATIC HYDROCARBONS

DIESEL	A
KEROSENE	S
UNLEADED GASOLINE	S
HYDRAULIC OIL	A
MOTOR OIL	A
CRUDE/SOUR CRUDE	A

AROMATICS, KEYTONES & CHLORINATED SOLVENTS

ALCOHOL, GRAIN 76.5%	S
HEXANE	D
XYLENE	D
MIBK	S
MEK	D
MAK	D
N-BUTANOL	D
IPA	D
TOLUENE	D

MISCELLANEOUS

SEWAGE	A
H ₂ S GAS	A
RAW WATER	A
SALT WATER	A
DE-IONIZED WATER	A
03	A

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. Manufacturer reserves the right to modify all data without prior notification or liability.